arXiv:1206.6993v1 [math.AP] 29 Jun 2012

On the relation between local and effective properties for planar elastic structures

Dag Lukkassen[*], Annette Meidell[*], and Klas Pettersson[†]

June 25, 2012

Abstract

In this paper we show an explicit relation between the local and the effective elastic properties for planar elastic structures, up to some purely geometric constants. The model considered is periodic structures with isotropic and homogeneous (or in a way uniformly shifted) local elasticity tensors in the linear theory of elasticity. Our study is restricted to the structures that have some bounded and connected periodicity cell with Lipschitz continuous boundary, that in addition have positive definite effective tensors. The result is a slight generalization of previous work by Vigdergauz that can be found in [25].

1 Introduction

In this paper we will be confined with effective elastic properties of periodic structures in the planar linear theory of elasticity. We show that the relation between the effective and local elastic properties for structures on Lipschitz domains is always elementary under the hypothesis of positive definite effective tensor and constant isotropic local tensor. This generalizes previous work by Vigdergauz. See [25]. A partial generalization was given in [13].

The periodic structures we will consider are the planar structures with locally isotropic elasticity tensors which are constant throughout the domain. The elastic hypothesis will be the linear theory in which both the strain mapping and the relation between stress and strain are supposed to be linear.

We will focus on a periodicity cell Ω of the structure to be studied. Apart from specifying an elasticity tensor on Ω, we will make the following geometric assumptions on the domain. Let Ω be a bounded and connected open set in $\mathbf{R}^2$ with Lipschitz continuous boundary. Moreover, we suppose that Ω is contained in some translation Y of the cell $(0, l_1) \times (0, l_2)$ for some $l_1, l_2 > 0$. Let $\widetilde{\Omega}$ be the periodic extension of the periodicity cell Ω, that is $\widetilde{\Omega} = \operatorname{Int}\operatorname{Cl}(\Omega + l_1\mathbf{Z} \times l_2\mathbf{Z})$. We assume that $\widetilde{\Omega}$ is connected and has Lipschitz continuous boundary, which additionally reduces the set of possible domains.

We say that a vector $u \in H^1(\Omega)^2$ is quasiperiodic if $u - \xi x \in H^1_{\mathrm{per}}(\Omega)^2$ for some $\xi \in \mathbf{R}^{2\times 2}$, where $H^1_{\mathrm{per}}(\Omega)^2$ denotes the closure in $H^1(\Omega)^2$ of[1] $C^\infty_{\mathrm{per}}(Y)^2$.

---

[*] Narvik University College, P.O. Box 385, N-8505 Narvik, Norway, and Norut Narvik, P.O. Box 250, N-8504 Narvik, Norway.

[†] Narvik University College, P.O. Box 385, N-8505 Narvik, Norway.

[1] The smooth functions on the 2-torus considered as functions on Y.

The matrix ξ is then, despite a slight risk of confusion, called the quasiperiod of u since the characteristic lengths l_1 and l_2 will be constant throughout.

For cartesian tensor fields we will use the following notation. The set of symmetric $n \times n$ real matrices is identified with $\mathbf{R}^{n(n-1)/2}$. The set of triclinic fourth order cartesian tensors is identified with $\mathbf{R}^6$, that is those a for which $a_{ijkl} = a_{jikl} = a_{klij}$ for all indices. Symmetric tensors are identified with symmetric matrices. The elements of $\mathbf{R}^6$ for which the matrix is positive definite will be denoted by E. The elasticity tensors will eventually be assumed to live in a subspace of the strongly elliptic ones $\mathcal{E}$, that is those a in the Lebesgue space of Ω with values in E such that[2] $\xi^2 \sim \xi a \xi$ on $\mathbf{R}^3$. Also, E is identified with its corresponding subspace of $\mathcal{E}$. An elasticity tensor $a \in \mathcal{E}$ is said to be square symmetric if $a_{1111} = a_{2222}$ and $a_{ii12} = 0$ for all i, and it is said to be isotropic if in addition $a_{1111} = a_{1122} + 2a_{1212}$. If $a \in \mathcal{E}$ is constant on Ω, it is called homogeneous; for example $a \in E$.

We will use the linear operators on $\mathcal{D}'(\Omega)^2$ obtained from the symmetric and antisymmetric parts of the gradient to model the linear strain and rotation of a displacement field u, respectively: $\nabla = \varepsilon + \omega$. The stress σ is assumed to be linearly related to the strain ε by some $a \in \mathcal{E}$ via the Hooke law: $\sigma = a\varepsilon$, provided the product is defined; componentwise,

$$\sigma_{ij} = \sum_{kl} a_{ijkl}\varepsilon_{kl}.$$

For convenience, when there is a displacement field u and an elasticity tensor a present, we will write just σ and ε for the stress $\sigma(u)$ and the strain $\varepsilon(u)$, respectively. Otherwise, σ may also denote some symbol in an equation that is not a priori coming from a displacement field.

The effective elasticity tensor is defined as follows. With $a \in \mathcal{E}$, let a^* be defined on $\mathbf{R}^3$ by the equation

$$a^*\xi = \frac{1}{|Y|}\int_\Omega \sigma^\xi \, dx, \tag{1}$$

where $\sigma^\xi = \sigma(u^\xi)$ for some quasiperiodic minimizer u^ξ of[3] $\int_\Omega \varepsilon(u)\cdot\sigma(u)\,dx$ with quasiperiod ξ. The above definition of a^* can be justified by the Riesz representation theorem and homogenization theory, see for example [17].

Throughout, the inverse of an elasticity tensor a will be denoted by $c = a^{-1}$, and c will be called the compliance tensor. The difference between two vectors depending on the elasticity tensor will be denoted by the addition of a prefix Δ. For example $\Delta c_{1111} = c^{(2)}_{1111} - c^{(1)}_{1111}$.

The first assertion in the following theorem is the main result of this paper.

---

[2] The asymptotic equivalence relation $\sim$ of which (a, b) is an element if there exists positive real constants κ_i such that $\kappa_1 a \leq b \leq \kappa_2 a$.

[3] The Dirichlet problem with linear boundary conditions.

Theorem 1. *Let $a \in E$ be a constant and isotropic elasticity tensor on Ω. Let a^* be the effective elasticity tensor defined by equation (1) with local tensor a. Suppose that a^* is positive definite. Then there exists $d \in \mathbf{R}^6$, which is independent of a, such that*

$$c^* = c_{1111}\, d + c_{1212}\, e,$$

where $e \in \mathbf{R}^6$ is defined by $e_{1212} = -2e_{1122} = 1$ with the rest of the components equal to zero. Relaxing to isotropic and smooth $a \in \mathcal{E}$, but requering that $\Delta c_{1122} = -2\Delta c_{1212} =$ constant, then

$$\Delta c^* = \Delta c_{1212}\, e = \Delta c.$$

A proof of Theorem 1 will be presented in Section 3. The following remarks concern the components of the tensor d and relations to common notation.

Remark 1. *The equation $\Delta c^* = \Delta c_{1212}\, e$ in Theorem 1 means that for isotropic and not necessarily constant compliance tensor c, a shift of c such that $\Delta c_{1122} = -2\Delta c_{1212} =$ constant, leads to precisely the same shift in the effective compliance tensor c^*. This is known (see for example Muskhelishvili's exposition on stress invariance in [16]). See also Remark 9 in this regard.*

Remark 2. *The components of d in Theorem 1 satisfy the following inequalities:*

$$\begin{aligned} d_{1111},\, d_{2222} &> 0, & d_{1212} &\geq 0, \\ d_{1111} + 2d_{1122} + d_{2222} &> 0, & d_{1111} - 2d_{1122} + d_{2222} &\geq 0, \\ d_{2222} + 4d_{2212} + 4d_{1212} &\geq 0, & d_{2222} - 4d_{2212} + 4d_{1212} &\geq 0, \\ d_{1111} + 4d_{1112} + 4d_{1212} &\geq 0, & d_{1111} - 4d_{1112} + 4d_{1212} &\geq 0. \end{aligned}$$

This is a direct consequence of the positive definiteness of the effective tensor.

Remark 3 (Matrix notation)**.** *In a common matrix*[4] *representation of elasticity tensor fields, the first assertion of Theorem 1 can be stated as follows: There exists a symmetric matrix D with constant real entries such that the effective compliance*[5] *tensor C^* satisfies*

$$\begin{pmatrix} C_1^* & C_2^* & C_3^* \\ C_2^* & C_4^* & C_5^* \\ C_3^* & C_5^* & C_6^* \end{pmatrix} = \left(\frac{1}{K} + \frac{1}{G}\right) \begin{pmatrix} D_1 & D_2 & D_3 \\ D_2 & D_4 & D_5 \\ D_3 & D_5 & D_6 \end{pmatrix} + \frac{1}{G} \begin{pmatrix} 0 & -1/2 & 0 \\ -1/2 & 0 & 0 \\ 0 & 0 & 1 \end{pmatrix},$$

where the constants K and G are local planar bulk modulus and the local shear modulus, respectively. Moreover, D does not depend on any of K and G.

In the case of plane stress or plane strain, where dimension reduction or decoupling has preceded the planar model, the local moduli K and G above are related to the Young modulus E and Poisson number ν as follows:

$$K = \frac{E}{2(1-\nu)}, \qquad \text{(plane stress)}$$

$$K = \frac{E}{2(1+\nu)(1-2\nu)}. \qquad \text{(plane strain)}$$

---

[4] The so-called contracted or Voigt notation. Explicitly, $C_1^* = c^*_{1111}$, $C_2^* = c^*_{1122}$, $C_3^* = 2c^*_{1112}$, $C_4^* = c^*_{2222}$, $C_5^* = 2c^*_{2212}$, $C_6^* = 4c^*_{1212}$, with the rest of the components implicitly defined by the triclinic symmetry. See Corollary 1 in Section 2 for a concrete example.

[5] The inverse C^* of the effective elasticity tensor, that is effectively $\varepsilon' = C^* \sigma'$.

In either case, the shear modulus G and the corresponding three-dimensional bulk modulus k satisfy

$$G = \frac{E}{2(1+\nu)}, \qquad\qquad k = K - \frac{G}{3}.$$

The Lamé moduli are related by $(\mu, \lambda) = (G, K - G)$. For definitions, we refer the reader to any standard reference on linear elasticity as for example [1, 2] or more specifically to [24, Appendix B].

We conclude this section with an example to motivate why the validity of the claimed result can be expected. Consider a smooth perforated periodic structure in $\mathbf{R}^2$ with constant and isotropic local compliance tensor C and with effective compliance tensor C^*. The classical Vigdergauz equations (see [25, Section 4]) can be written on the form

$$(C_1^*, C_2^*, C_6^*) = C_1(D_1, D_2, D_6) + C_2(E_1, E_2, E_6),$$

where D_i are suitable linear combinations of the Vigdergauz constants, which are independent of the local compliance tensor C, and E_i are constant matrices independent of both C and the geometry of the holes. A natural guess of the general form of this relation can therefore be

$$C^* = C_1 D + C_2 E, \tag{2}$$

for some matrix D independent of C, and some independent constant matrix E. An equivalent formulation, by the local isotropy, is $C^* = C_1 D' + C_6 E'$, with matrices D' and E' corresponding to D and E, respectively, which up to scaling is the form we have used in the formulations above (Theorem 1 and Remark 3).

The result referred to in the previous paragraph is a generalization for constant isotropic tensors of the observation that if the local compliance tensor is changed from C to C' in such a way that $C_2' - C_2 = 2(C_6 - C_6') = \text{constant}$, then the effective compliance tensor is shifted from C^* to $(C^*)'$ in the very same way. This means that

$$(C^*)' - C^* = (C_6' - C_6)E,$$

which agrees with equation (2) if C is constant on Ω since the above shift implies $C_1' - C_1 = 0$ by isotropy. Cherkaev, Lurie, and Milton gave a proof of this result in [6]. As a part of the proof of Theorem 1, we provide an alternative proof of this.

In the next section some direct consequences of the result will be laid out before we present a proof in Section 3.

2 Square symmetry

In this section we present a particular case of the main result (Theorem 1) in which the effective tensor that have additional structural symmetry. In this way we can relate our result to previous investigations. We remark that the corollary below generalizes the corresponding cited results. The references are included in the end of this section. We will here restrict our attention to the effective tensors which have a square symmetric structure, that is the effective tensor a^*_{ijkl} satisfies $a^*_{1111} = a^*_{2222}$, and $a^*_{1112} = a^*_{2212} = 0$.

Knowledge about the structure of the effective tensor can sometimes be acquired a priori by identification of symmetry groups of the periodicity cell for which the inner product, corresponding to the Riesz representation of the elastic energy functional, is in a suitable sense invariant (see any standard reference on Fourier analysis and representations of groups of finite order, and for this particular application, see for example [5, 14, 20, 22]). The standard example here is the square honeycomb, with a homogeneous and isotropic local elasticity tensor, for which the symmetry group is the dihedral group Dih_4 of order 8.

Corollary 1 (Square symmetry)**.** *Let the local elasticity tensor be isotropic. Then in terms of the planar bulk modulus K and shear modulus G, it may be represented*[6] *by the matrix*

$$\begin{pmatrix} K+G & K-G & 0 \\ K-G & K+G & 0 \\ 0 & 0 & G \end{pmatrix}.$$

Suppose that the effective tensor has square symmetry, which means that it may be represented by a matrix of the form

$$\begin{pmatrix} K^*+G^* & K^*-G^* & 0 \\ K^*-G^* & K^*+G^* & 0 \\ 0 & 0 & G^*_{45} \end{pmatrix}, \tag{3}$$

where K^* is the effective planar bulk modulus, and G^* and G^*_{45} are the effective shear moduli. Suppose that K^*, G^*, $G^*_{45} > 0$, which is true if and only if the matrix is positive definite. Then there exist nonnegative real numbers A_1, A_2, A_3, that do not depend on the local elastic properties K and G, such that

$$\begin{aligned} \frac{1}{K^*} &= \frac{1}{K} + A_1\left(\frac{1}{K} + \frac{1}{G}\right), \\ \frac{1}{G^*} &= \frac{1}{G} + A_2\left(\frac{1}{K} + \frac{1}{G}\right), \\ \frac{1}{G^*_{45}} &= \frac{1}{G} + A_3\left(\frac{1}{K} + \frac{1}{G}\right). \end{aligned}$$

Proof. Since the effective elasticity tensor, call it B^*, is assumed to be square symmetric, it can be written on the form (3). The compliance tensor $C^* = (B^*)^{-1}$ is therefore of the same form (the same entries are zero in general). The validity of the three equations in Corollary 1 then follows from the equation in Remark 3 (see also Remark 4 below). $\square$

The result of Corollary 1 is the Vigdergauz equations for the studied class of structures. The nonnegativity of the constants A_1, A_2, A_3 follows from the assumption that the effective tensor is positive definite. We also refer the reader to [13, 25]. To conclude this section two remarks on the geometric constants are included.

---

[6] See Remark 3.

Remark 4. *The explicit relationship between the entries* D_i *of the matrix* D *in Remark 3 and the Vigdergauz constants* A_1*,* A_2*,* A_3 *for square symmetric effective tensors, is by Corollary 1 given by*

$$D_1 = D_4 = \frac{1 + A_1 + A_2}{4}, \quad D_3 = D_5 = 0, \quad D_2 = \frac{1 + A_1 - A_2}{4}, \quad D_6 = A_3.$$

In the case of effective isotropy, $D_6 = A_2$*, so then we have the additional dependence* $D_6 = 2(D_1 - D_2)$*.*

Remark 5. *We note that by Theorem 1, the effective tensor* a^* *is an elementary function of the components of the local isotropic constant tensor* a*. For example, for a square symmetric effective tensor it follows from Corollary 1 that* $\nabla_{(K,G)} K^* = g(1 + A_1, A_1)$*,* $\nabla_{(K,G)} G^* = g(A_2, 1 + A_2)$*,* $\nabla_{(K,G)} G^*_{45} = g(A_3, 1 + A_3)$*, where* $g(p, q) = (qK + pG)^{-2}(pG^2, qK^2)$*. Thus in this case the effective parameters are monotonically increasing functions of the local parameters* K *and* G*. In particular,* K^* *is strictly increasing in* K*, and* G^* *and* G^*_{45} *are strictly increasing in* G*. For* $\Omega \neq Y$*, the rest of the dependencies are strictly increasing as well, where* A_1*,* A_2*,* $A_3 > 0$ *for* $\Omega \neq Y$ *in Corollary 1 follows for example from the Hashin-Shtrikman bounds. See [4].*

3 Proof of Theorem 1

In this section we will give a proof of Theorem 1. First we state and prove two preliminary lemmas on the relation between average stresses and quasiperiods for the displacement fields involved in the definition of the effective tensor.

For the proof we will make use of curves connecting opposite sides of the cell Ω. Let γ_1 be a smooth curve connecting two points in $\overline{\Omega}$ with l_1 as the difference between the x_1 components, and with equal x_2 components. We assume that γ_1 is separated from any possible hole in the global structure, that is $\operatorname{dist}(\gamma_1, \partial\widetilde{\Omega}) > 0$. Moreover, we suppose that the x_1 component of the unit tangent τ to γ_1 is always positive. Such a curve γ_1 exists by the connectedness of Ω and its periodic extension $\widetilde{\Omega}$. Let γ_2 be an analogue curve in the x_2 direction, by interchanging all the indices. An illustration of a possible pair of curves γ_1 and γ_2 for a periodicity cell Ω is shown in Figure 1(a).

The following lemma is a variant of the classical Cesàro formula. We will use the notation

$$\varsigma_{ij} = \begin{cases} 0, & \text{if } i = j, \\ 1, & \text{otherwise.} \end{cases}$$

Lemma 1 (Quasiperiods)**.** *Let* $a \in \mathcal{E}$ *be an elasticity tensor. Let* u *be quasiperiodic on* Ω *with quasiperiod* $\xi \in \mathbf{R}^{2\times 2}$*. Suppose that* a *and* u *are smooth in some neighborhood of* γ_i*. Then*

$$\begin{aligned} &\xi_{ij} + \omega_{ji}(\alpha) \\ &= \frac{1}{l_i} \sum_{qrst} \Big(\frac{1}{2} \int_{\gamma_i} c_{jrst} \sigma_{st} \, dx_r + \varsigma_{rj} \int_{\gamma_i} \frac{\partial (c_{rqst} \sigma_{st})}{\partial x_j} x_r \, dx_q - \varsigma_{rj} \int_{\gamma_i} \frac{\partial (c_{jqst} \sigma_{st})}{\partial x_r} x_r \, dx_q \Big), \end{aligned}$$

where $c = a^{-1}$ *and* α *is the starting point of the integration along* γ_i*.*

Proof. Since u is quasiperiodic and smooth in a neighborhood of γ_i, and the endpoints α and β of γ_i have equal components except for the $i$ths, we have by the Newton-Leibniz formula,

$$\xi_{ij} l_i = u_j(\beta) - u_j(\alpha) = \Big(\int_{\gamma_i} \nabla u \, dx\Big)_j = \Big(\int_{\gamma_i} \varepsilon \, dx\Big)_j + \Big(\int_{\gamma_i} \omega \, dx\Big)_j .$$

By the linear relation between ε and σ, and the nonsingularity of the elasticity tensor a, we have

$$\Big(\int_{\gamma_i} \varepsilon \, dx\Big)_j = \int_{\gamma_i} \sum_r \varepsilon_{jr} \, dx_r = \sum_{rst} \int_{\gamma_i} c_{jrst}\sigma_{st} \, dx_r. \tag{4}$$

By the smoothness of u, an integration by parts yields

$$\begin{aligned}\Big(\int_{\gamma_i} \omega \, dx\Big)_j &= \int_{\gamma_i} \sum_r \omega_{jr} \, dx_r = \sum_r (\beta_r - \alpha_r)\omega_{jr}(\alpha) - \sum_{kr} \int_{\gamma_i} \frac{\partial \omega_{jr}}{\partial x_k} x_r \, dx_k \\ &= l_i \omega_{ji}(\alpha) + \sum_{kr, r\neq j} \int_{\gamma_i} \frac{\partial \omega_{rj}}{\partial x_k} x_r \, dx_k,\end{aligned}$$

where we in the second step used that ω is periodic since u is quasiperiodic. By noting that

$$\frac{\partial \omega_{rj}}{\partial x_k} = \frac{\partial \varepsilon_{rk}}{\partial x_j} - \frac{\partial \varepsilon_{jk}}{\partial x_r},$$

we find

$$\begin{aligned}\int_{\gamma_i} \frac{\partial \omega_{rj}}{\partial x_k} x_r \, dx_k &= \int_{\gamma_i} \Big(\frac{\partial \varepsilon_{rk}}{\partial x_j} - \frac{\partial \varepsilon_{jk}}{\partial x_r}\Big) x_r \, dx_k \\ &= \int_{\gamma_i} \sum_{st} \bigg(\frac{\partial (c_{rkst}\sigma_{st})}{\partial x_j} - \frac{\partial (c_{jkst}\sigma_{st})}{\partial x_r}\bigg) x_r \, dx_k \\ &= \sum_{st} \Big(\int_{\gamma_i} \frac{\partial (c_{rkst}\sigma_{st})}{\partial x_j} x_r \, dx_k - \int_{\gamma_i} \frac{\partial (c_{jkst}\sigma_{st})}{\partial x_r} x_r \, dx_k\Big).\end{aligned}$$

Thus

$$\Big(\int_{\gamma_i} \omega \, dx\Big)_j = l_i \omega_{ji}(\alpha) + \sum_{\substack{krst \\ r\neq j}} \Big(\int_{\gamma_i} \frac{\partial (c_{rkst}\sigma_{st})}{\partial x_j} x_r \, dx_k - \int_{\gamma_i} \frac{\partial c_{jkst}\sigma_{st}}{\partial x_r} x_r \, dx_k\Big).$$

This together with equation (4) give the asserted equality. ☐

Remark 6. *Note that the local elasticity tensor a in Lemma 1 need not be isotropic. Moreover, the lemma is true as it is stated for the analogue hypothesis in $\mathbf{R}^n$ for $n \geq 2$, if the factor $1/2$ is replaced by $1/n$ on the right hand side in the equation.*

Let U be a connected and open set in $\mathbf{R}^n$ with Lipschitz continuous boundary. The following version of the Green formula on $H(\mathrm{div}, U) \times H^1(U) \ni (v, \varphi)$ holds:

$$\int_U v \cdot \nabla \varphi \, dx + \int_U \mathrm{div}\, v \cdot \varphi \, dx = \langle v\nu, \varphi \rangle, \tag{5}$$

where $H(\mathrm{div}, U)$ denotes the space of elements of $L^2(U)^2$ with with $\mathrm{div}\, v$ in $L^2(U)$, and $\langle \cdot, \cdot \rangle$ denotes the pairing of $H^{1/2}(\partial U)$ and its continuous dual. See [11] for a construction of such a trace mapping.



(a) (b) (c)

Figure 1: (a) A periodicity cell Ω with curves γ_1 and γ_2. (b) Translations γ_1' and γ_2' of γ_1 and γ_2, respectively. (c) The domain Ω', with outer boundary Γ corresponding to the curves in (a) and (b); Ω' has no cusps.



Figure 2: An interior part of a periodically perforated structure.

We will make use of the following curves in the extended domain. Let γ_1' be the translate of γ_1 such that the left endpoint of γ_1' is the common point of γ_1 and γ_2. Then let γ_2' be the translate of γ_2 such that its lower endpoint is the left endpoint of γ_1'. Let Y' be a translate of Y such that γ_1' and γ_2' are the lower and left sides of the boundary of $Y' \cap \Lambda$, respectively. Let Ω' be the intersection of $\widetilde{\Omega}$ and the region of $\mathbf{R}^2$ bounded by

$$\Gamma := \gamma_1' \cup \gamma_2' \cup (0, l_2) + \gamma_1' \cup (l_1, 0) + \gamma_2'.$$

Illustrations of such curves and domains are shown in Figure 1(a)–(c) for the periodically perforated structure shown in Figure 2.

Lemma 2 (Average stress)**.** *Let the local elasticity tensor in $\mathcal{E}$ be smooth on Ω and Y-periodic. Suppose that u is a quasiperiodic minimizer of $\int_\Omega \varepsilon(u)\cdot\sigma(u)\,dx$. Then for $i \neq j$,*

$$\int_\Omega \sigma_{ii}\,dx = l_i \int_{\gamma_j} (\sigma\nu)_i\,dx, \qquad\qquad \int_\Omega \sigma_{ij}\,dx = l_j \int_{\gamma_i} (\sigma\nu)_i\,dx.$$

Proof. Since u is quasiperiodic and minimizes the elastic energy, u is the unique solution, up to translation, to the equation

$$\begin{aligned} \operatorname{div}\sigma &= 0 \text{ in } \mathcal{D}'(\widetilde{\Omega})^2, \\ \sigma\nu &= 0 \text{ in } H^{-1/2}(\partial\widetilde{\Omega})^2. \end{aligned}$$

Since σ and $\operatorname{div}\sigma$ have components in $L^2(\Omega')$, it follows from the Green formula (5) that

$$\int_{\Omega'} (\sigma_{11},\sigma_{12})\cdot\nabla\varphi\,dx + \int_{\Omega'} \operatorname{div}(\sigma_{11},\sigma_{12})\,\varphi\,dx = \langle(\sigma\nu)_1,\varphi\rangle,$$

for any $\varphi \in H^1(\Omega')$. By the regularity of u and the vanishing of $\sigma\nu$ on $\partial\widetilde{\Omega}$, we have that $\sigma\nu \in L^2(\partial\Omega')^2$. See [9]. Hence

$$\begin{aligned} \langle(\sigma\nu)_1,\varphi\rangle &= \int_{\partial\Omega'} (\sigma\nu)_1\,\varphi\,dx = \int_\Gamma (\sigma\nu)_1\,\varphi\,dx \\ &= \int_{\gamma_1'} (\sigma\nu)_1\,\varphi\,dx + \int_{(0,l_2)+\gamma_1'} (\sigma\nu)_1\,\varphi\,dx + \int_{\gamma_2'} (\sigma\nu)_1\,\varphi\,dx + \int_{(l_1,0)+\gamma_2'} (\sigma\nu)_1\,\varphi\,dx \\ &= \int_{\gamma_1'} (\sigma\nu)_1\,(\varphi(x)-\varphi(x_1,x_2-l_2))\,dx + \int_{\gamma_2'} (\sigma\nu)_1\,(\varphi(x)-\varphi(x_1-l_1,x_2))\,dx, \end{aligned}$$

where we in the last step made a change of variables and used the periodicity of σ and the opposite signs of the outward unit normals.

Let $\varphi = x_1$. Then $\varphi(x_1,x_2-l_2) = \varphi(x)$ and $\varphi(x)-\varphi(x_1-l_1,x_2) = l_1$. Thus

$$\langle(\sigma\nu)_1,\varphi\rangle = l_1 \int_{\gamma_2'} (\sigma\nu)_1\,dx = l_1 \int_{\gamma_2} (\sigma\nu)_1\,dx,$$

where we in the last step used the periodicity of σ. Since $\nabla\varphi = (1,0)$ and $\operatorname{div}\sigma = 0$, we have by periodicity and the Green formula that

$$\int_\Omega \sigma_{11}\,dx = \int_{\Omega'} \sigma_{11}\,dx = l_1 \int_{\gamma_2} (\sigma\nu)_1\,dx. \tag{6}$$

With $\varphi = x_2$, we obtain in the same way,

$$\int_\Omega \sigma_{12}\,dx = l_2 \int_{\gamma_1} (\sigma\nu)_1\,dx. \tag{7}$$

By the symmetry with respect to the indices, the equations corresponding to the equations (6) and (7) are

$$\int_\Omega \sigma_{22}\,dx = l_2 \int_{\gamma_1} (\sigma\nu)_2\,dx, \qquad\qquad \int_\Omega \sigma_{12}\,dx = l_1 \int_{\gamma_2} (\sigma\nu)_2\,dx,$$

which completes the proof. □

Now we shall specialize Lemma 1 to the case of constant and isotropic local elasticity tensors. We will use[7] the following notation for scalar ϕ and vector-valued φ:

$$\operatorname{curl}\phi = \left(\frac{\partial\phi}{\partial x_2}, -\frac{\partial\phi}{\partial x_1}\right), \qquad \operatorname{curl}\varphi = \frac{\partial\varphi_2}{\partial x_1} - \frac{\partial\varphi_1}{\partial x_2},$$

which is the reason for the slight antisymmetry in the following formulas, with respect to the indices.

Lemma 3 (Quasiperiods for constant isotropic tensors)**.** *Under the hypotheses of Lemma 1, suppose that a is constant and isotropic, ξ is symmetric, and that* $\operatorname{div}\sigma = 0$ *on* $\gamma_1 \cup \gamma_2$*. Then*

$$\begin{aligned}
\xi_{11} &= -\frac{2c_{1212}}{|Y|}\int_\Omega \sigma_{22}\,dx + \frac{c_{1111}}{l_1}\int_{\gamma_1}((\operatorname{Tr}\sigma, 0) - x_2 \operatorname{curl}\operatorname{Tr}\sigma)\,dx,\\
\xi_{22} &= -\frac{2c_{1212}}{|Y|}\int_\Omega \sigma_{11}\,dx + \frac{c_{1111}}{l_2}\int_{\gamma_2}((0, \operatorname{Tr}\sigma) + x_1 \operatorname{curl}\operatorname{Tr}\sigma)\,dx,\\
\xi_{12} &= \frac{2c_{1212}}{|Y|}\int_\Omega \sigma_{12}\,dx + \frac{c_{1111}}{2l_1}\int_{\gamma_1'}((\operatorname{Tr}\sigma, 0) + x_1 \operatorname{curl}\operatorname{Tr}\sigma)\,dx\\
&\qquad + \frac{c_{1111}}{2l_2}\int_{\gamma_2'}((0, \operatorname{Tr}\sigma) - x_2 \operatorname{curl}\operatorname{Tr}\sigma)\,dx.
\end{aligned}$$

Proof. By Lemma 1 we have

$$\xi_{11}l_1 = \sum_{rst}\int_{\gamma_1} c_{1rst}\sigma_{st}\,dx_r + \sum_{qst}\left(\int_{\gamma_1} c_{2qst}\frac{\partial\sigma_{st}}{\partial x_1}x_2\,dx_q - \int_{\gamma_1} c_{1qst}\frac{\partial\sigma_{st}}{\partial x_2}x_2\,dx_q\right).$$

Since a is isotropic,

$$c_{1111} = c_{2222}, \qquad c_{1111} = c_{1122} + 2c_{1212}, \qquad c_{1112} = c_{2212} = 0.$$

By Lemma 2 we have

$$\begin{aligned}
\frac{1}{l_2}\int_\Omega \sigma_{22}\,dx &= \int_{\gamma_1}(\sigma\nu)_2\,dx = \int_{\gamma_1}\sigma_{22}\,dx_1 - \int_{\gamma_1}\sigma_{12}\,dx_2,\\
\frac{1}{l_1}\int_\Omega \sigma_{11}\,dx &= \int_{\gamma_2}(\sigma\nu)_1\,dx = \int_{\gamma_2}\sigma_{11}\,dx_2 - \int_{\gamma_2}\sigma_{12}\,dx_1.
\end{aligned}$$

---

[7] This double notation (ω and curl) for the so-called rotation of vector fields with values in $\mathbf{R}^2$ is motivated by the standard notation, since we will here not be concerned with specific components.

The representation of ξ_{11} is obtained by the following calculation:

$$\begin{aligned}
\xi_{11} l_1 &= c_{1111} \int_{\gamma_1} \sigma_{11}\, dx_1 + c_{1122} \int_{\gamma_1} \sigma_{22}\, dx_1 + 2c_{1212} \int_{\gamma_1} \sigma_{12}\, dx_2 \\
&\quad + 2c_{1212} \int_{\gamma_1} \frac{\partial \sigma_{12}}{\partial x_1} x_2\, dx_1 + c_{1122} \int_{\gamma_1} \frac{\partial \sigma_{11}}{\partial x_1} x_2\, dx_2 + c_{1111} \int_{\gamma_1} \frac{\partial \sigma_{22}}{\partial x_1} x_2\, dx_2 \\
&\quad - c_{1111} \int_{\gamma_1} \frac{\partial \sigma_{11}}{\partial x_2} x_2\, dx_1 - c_{1122} \int_{\gamma_1} \frac{\partial \sigma_{22}}{\partial x_2} x_2\, dx_1 - 2c_{1212} \int_{\gamma_1} \frac{\partial \sigma_{12}}{\partial x_2} x_2\, dx_2 \\
&= c_{1111} \int_{\gamma_1} \sigma_{11}\, dx_1 + (c_{1111} - 2c_{1212}) \int_{\gamma_1} \sigma_{22}\, dx_1 + 2c_{1212} \int_{\gamma_1} \sigma_{12}\, dx_2 \\
&\quad + 2c_{1212} \int_{\gamma_1} \frac{\partial \sigma_{12}}{\partial x_1} x_2\, dx_1 + (c_{1111} - 2c_{1212}) \int_{\gamma_1} \frac{\partial \sigma_{11}}{\partial x_1} x_2\, dx_2 \\
&\quad + c_{1111} \int_{\gamma_1} \frac{\partial \sigma_{22}}{\partial x_1} x_2\, dx_2 - c_{1111} \int_{\gamma_1} \frac{\partial \sigma_{11}}{\partial x_2} x_2\, dx_1 \\
&\quad - (c_{1111} - 2c_{1212}) \int_{\gamma_1} \frac{\partial \sigma_{22}}{\partial x_2} x_2\, dx_1 - 2c_{1212} \int_{\gamma_1} \frac{\partial \sigma_{12}}{\partial x_2} x_2\, dx_2 \\
&= c_{1111} \int_{\gamma_1} \operatorname{Tr} \sigma\, dx_1 + c_{1111} \int_{\gamma_1} \frac{\partial \operatorname{Tr} \sigma}{\partial x_1} x_2\, dx_2 - c_{1111} \int_{\gamma_1} \frac{\partial \operatorname{Tr} \sigma}{\partial x_2} x_2\, dx_1 \\
&\quad - 2c_{1212} \left(\frac{1}{l_2} \int_\Omega \sigma_{22}\, dx - \int_{\gamma_1} (\operatorname{div} \sigma)_2 x_2\, dx_1 + \int_{\gamma_1} (\operatorname{div} \sigma)_1 x_2\, dx_2 \right) \\
&= c_{1111} \int_{\gamma_1} ((\operatorname{Tr} \sigma, 0) - x_2 \operatorname{curl} \operatorname{Tr} \sigma)\, dx - \frac{2c_{1212}}{l_2} \int_\Omega \sigma_{22}\, dx,
\end{aligned}$$

where we in the last step used $\operatorname{div} \sigma = 0$. By the same procedure, we find

$$\xi_{22} l_2 = c_{1111} \int_{\gamma_2} ((0, \operatorname{Tr} \sigma) + x_1 \operatorname{curl} \operatorname{Tr} \sigma)\, dx - \frac{2c_{1212}}{l_1} \int_\Omega \sigma_{11}\, dx,$$

from which the representation of ξ_{22} follows.

We turn to ξ_{12}. Let a denote the common point of γ_1 and γ_2. By Lemma 2 and the periodicity we have

$$\begin{aligned}
\frac{1}{l_2} \int_\Omega \sigma_{12}\, dx &= \int_{\gamma_1'} (\sigma \nu)_1\, dx = \int_{\gamma_1'} \sigma_{12}\, dx_1 - \int_{\gamma_1'} \sigma_{11}\, dx_2, \\
\frac{1}{l_1} \int_\Omega \sigma_{12}\, dx &= \int_{\gamma_2'} (\sigma \nu)_2\, dx = \int_{\gamma_2'} \sigma_{12}\, dx_2 - \int_{\gamma_2'} \sigma_{22}\, dx_1.
\end{aligned}$$

By periodicity it follows from Lemma 1 that

$$
\begin{aligned}
&(\xi_{12}+\omega_{21}(\alpha))l_1 \\
&\quad = 2c_{1212}\int_{\gamma_1'}\sigma_{12}\,dx_1 + (c_{1111}-2c_{1212})\int_{\gamma_1'}\sigma_{11}\,dx_2 + c_{1111}\int_{\gamma_1'}\sigma_{22}\,dx_2 \\
&\qquad + c_{1111}\int_{\gamma_1'}\frac{\partial\sigma_{11}}{\partial x_2}x_1\,dx_1 + (c_{1111}-2c_{1212})\int_{\gamma_1'}\frac{\partial\sigma_{22}}{\partial x_2}x_1\,dx_1 \\
&\qquad + 2c_{1212}\int_{\gamma_1'}\frac{\partial\sigma_{12}}{\partial x_2}x_1\,dx_2 - 2c_{1212}\int_{\gamma_1'}\frac{\partial\sigma_{12}}{\partial x_1}x_1\,dx_1 \\
&\qquad - (c_{1111}-2c_{1212})\int_{\gamma_1'}\frac{\partial\sigma_{11}}{\partial x_1}x_1\,dx_2 - c_{1111}\int_{\gamma_1'}\frac{\partial\sigma_{22}}{\partial x_1}x_1\,dx_2 \\
&\quad = c_{1111}\int_{\gamma_1'}\operatorname{Tr}\sigma\,dx_2 + c_{1111}\int_{\gamma_1'}\frac{\partial\operatorname{Tr}\sigma}{\partial x_2}x_1\,dx_1 - c_{1111}\int_{\gamma_1'}\frac{\partial\operatorname{Tr}\sigma}{\partial x_1}x_1\,dx_2 \\
&\qquad + 2c_{1212}\left(\frac{1}{l_2}\int_\Omega\sigma_{12}\,dx - \int_{\gamma_1'}(\operatorname{div}\sigma)_2\,x_1\,dx_1 + \int_{\gamma_1'}(\operatorname{div}\sigma)_1\,x_1\,dx_2\right) \\
&\quad = c_{1111}\int_{\gamma_1'}((0,\operatorname{Tr}\sigma)+x_1\operatorname{curl}\operatorname{Tr}\sigma)\,dx + \frac{2c_{1212}}{l_2}\int_\Omega\sigma_{12}\,dx.
\end{aligned}
$$

Similarly,

$$
(\xi_{21}+\omega_{12}(\alpha))l_2 = c_{1111}\int_{\gamma_2'}((\operatorname{Tr}\sigma,0)-x_2\operatorname{curl}\operatorname{Tr}\sigma)\,dx + \frac{2c_{1212}}{l_1}\int_\Omega\sigma_{12}\,dx.
$$

Since $\xi\in\mathbf{R}^3$ and ω is antisymmetric, we have

$$
\begin{aligned}
2\xi_{12} = {} & \frac{c_{1111}}{l_1}\int_{\gamma_1'}((\operatorname{Tr}\sigma,0)+x_1\operatorname{curl}\operatorname{Tr}\sigma)\,dx \\
& + \frac{c_{1111}}{l_2}\int_{\gamma_2'}((0,\operatorname{Tr}\sigma)-x_2\operatorname{curl}\operatorname{Tr}\sigma)\,dx + \frac{4c_{1212}}{|Y|}\int_\Omega\sigma_{12}\,dx,
\end{aligned}
$$

which completes the proof. □

For the uniform shifts we will need the following version of the above lemma.

Lemma 4 (Quasiperiods for uniformly shifted isotropic tensors)**.** *Under the hypotheses of Lemma 1, suppose that a is isotropic, ξ is symmetric, and that* $\operatorname{div}\sigma = 0$ *on $\gamma_1\cup\gamma_2$. Assume that c is shifted in such a way that $\Delta c_{1122} = -2\Delta c_{1212} =$ constant. Then*

$$
\begin{aligned}
\Delta\xi_{11} &= -\frac{2\Delta c_{1212}}{|Y|}\int_\Omega\sigma_{22}\,dx, \\
\Delta\xi_{22} &= -\frac{2\Delta c_{1212}}{|Y|}\int_\Omega\sigma_{11}\,dx, \\
\Delta\xi_{12} &= \frac{2\Delta c_{1212}}{|Y|}\int_\Omega\sigma_{12}\,dx.
\end{aligned}
$$

Proof. By considering the differences $\Delta\xi_{ij}$ and carrying out the same calculations as in the proof of Lemma 3, the result is obtained by noting that the supposed shift for isotropic c means, in particular, that $\Delta c_{1111} = 0$. □

For presentation purpose, we include a fundamental lemma which is sometimes attributed[8] to Michell and it is concerned with the dependence of the stress on the elasticity tensor for the Neumann problem. See [15]. This is the reason why we restrict our analysis to two dimensions. The version we are interested in can be stated as follows.

Lemma 5 (Michell lemma)**.** *Let the elasticity tensor* $a \in \mathcal{E}$ *be smooth and isotropic on a bounded and connected Lipschitz domain* Ω *in* $\mathbf{R}^2$*. Then the stress* σ *does not depend on the elasticity tensor in the pure Neumann problem on* Ω *with* $\langle \sigma\nu, 1\rangle_\Gamma = 0$ *for all connected components* Γ *of* $\partial\Omega$*,*

(i) if a *is constant, or*

(ii) if $\Delta c_{1122} = -2\Delta c_{1212} =$ *constant.*

In (i) the condition on the data is necessary if $\Delta(a/a_{1111}) \neq 0$*. On the other hand, if* a *is constant and* $\Delta(a/a_{1111}) = 0$*, the condition on the data can be relaxed to just equilibrium,* $\langle \sigma\nu, 1\rangle_{\partial\Omega} = 0$*, and the stress does not depend on the specific components of the elasticity tensor.*

Remark 7. *The property* $\Delta(a/a_{1111}) \neq 0$ *means that two constant elasticity tensors are not scalar multiples of each other, which is the case if and only if* $\Delta(c_{1122}/c_{1111}) \neq 0$*. See also Remark 9.*

Before giving a proof of the lemma we make some additional technical remarks. The boundary data in Lemma 5 should be understood to belong to $H^{-1/2}(\Gamma_i)$ and is naturally assumed to satisfy $\sum_i \langle \sigma\nu, 1\rangle_{\Gamma_i} = 0$ in either case. Here $\langle \cdot, \cdot\rangle_{\Gamma_i}$ denotes the pairing of $H^{1/2}(\Gamma_i)^2$ and its continuous dual, where Γ_i are the connected components of $\partial\Omega$ with Γ_0 being the outer part.

By the supposed connectedness of Ω, an element $v \in L^2(\Omega)^2$ satisfies $\operatorname{div} v = 0$ and $\langle v\nu, 1\rangle_{H^{1/2}(\Gamma_i)} = 0$ if and only if there exists a unique $\phi \in H^1(\Omega)/\mathbf{R}$ such that $v = \operatorname{curl}\phi$. Moreover, the following Helmholtz type decomposition holds:

$$L^2(\Omega)^2 = \operatorname{curl}\left\{\phi \in H^1(\Omega) : \phi_{|\Gamma_0} = 0,\, \phi_{|\Gamma_i} = \text{constant}\right\} \oplus \nabla H^1(\Omega) \tag{8}$$

where the sum is direct. Proofs of these characterizations can be found in [11, Chapter 2].

We will also make use of a necessary and sufficient compatibility condition on symmetric $v_{ij} \in L^2(\Omega)$ that guarantees the existence of some displacement field $u \in H^1(\Omega)^2$ such that $v = \varepsilon(u)$. We will call the condition the Donati[9] lemma and it can be stated as

$$\sum_{ij} \int_\Omega v_{ij} s_{ij}\, dx = 0, \tag{9}$$

for all symmetric s with components, by density, in $C_0^\infty(\Omega)$ and such that $\operatorname{div} s = 0$. See [3, 8, 23].

Remark 8. *Note that* Ω *is not required to be simply connected in the Donati lemma, only connected, bounded, and open in* $\mathbf{R}^2$*, and with Lipschitz continuous boundary, in contrast to the classical St. Venant condition. See [7] and [12, page 40].*

---

[8] See [16, Chapter 5] for some historical remarks.

[9] Sometimes attributed to Donati in this context.

Proof of Lemma 5. By an argument by Fréchet and Riesz ([10, 21]), there exists a unique $u \in H^1(\Omega)^2/\ker(\varepsilon)$ such that

$$\begin{aligned} \operatorname{div}\sigma &= 0 \text{ in } \mathcal{D}'(\Omega)^2, \\ \sigma\nu &= g_i \text{ in } H^{-1/2}(\Gamma_i)^2, \end{aligned}$$

for any such g_i satisfying $\langle g_i, 1\rangle_{\Gamma_i} = 0$. Let σ be the solution to the above problem for some given g_i with constant and isotropic elasticity tensor on Ω. Then σ has components in $L^2(\Omega)$ and thus there exists $\phi \in H^1(\Omega)^2$ such that

$$\sigma_{11} = \frac{\partial\phi_1}{\partial x_2}, \qquad \sigma_{22} = -\frac{\partial\phi_2}{\partial x_1}, \qquad \sigma_{12} = -\frac{\partial\phi_1}{\partial x_1} = \frac{\partial\phi_2}{\partial x_2}, \tag{10}$$

where the last equation comes from the symmetry of σ. The condition (9) can be written as follows in terms of ϕ, for any symmetric s with components in $C_0^\infty(\Omega)$ satisfying $\operatorname{div} s = 0$,

$$0 = -\sum_{ij}\int_\Omega \varepsilon_{ij}s_{ij}\,dx = c_{1111}\int_\Omega \operatorname{curl}\phi \operatorname{Tr} s\,dx.$$

Indeed,

$$\begin{aligned} \sum_{ij}\varepsilon_{ij}s_{ij} &= \sum_{ijkl} c_{ijkl}\sigma_{kl}s_{ij} \\ &= (c_{1111}\sigma_{11} + c_{1122}\sigma_{22})s_{11} + (c_{1122}\sigma_{11} + c_{1111}\sigma_{22})s_{22} + 4c_{1212}\sigma_{12}s_{12} \\ &= c_{1111}\left(\frac{\partial\phi_1}{\partial x_2} - \frac{\partial\phi_2}{\partial x_1}\right)(s_{11}+s_{22}) \\ &\quad + 2c_{1212}\left(\frac{\partial\phi_2}{\partial x_1}s_{11} + \frac{\partial\phi_2}{\partial x_2}s_{12} - \frac{\partial\phi_1}{\partial x_1}s_{12} - \frac{\partial\phi_1}{\partial x_2}s_{22}\right), \end{aligned}$$

where we in the last step used the equations in (10) and the isotropy $c_{1111} = c_{1122} + 2c_{1212}$. Moreover,

$$\int_\Omega \left(\frac{\partial\phi_2}{\partial x_1}s_{11} + \frac{\partial\phi_2}{\partial x_2}s_{12}\right)dx = -\int_\Omega \phi_2\left(\frac{\partial s_{11}}{\partial x_1} + \frac{\partial s_{12}}{\partial x_2}\right)dx = 0,$$

and

$$\int_\Omega \left(\frac{\partial\phi_1}{\partial x_1}s_{12} + \frac{\partial\phi_1}{\partial x_2}s_{22}\right)dx = -\int_\Omega \phi_1\left(\frac{\partial s_{12}}{\partial x_1} + \frac{\partial s_{22}}{\partial x_2}\right)dx = 0,$$

where both integrals vanish because $\operatorname{div} s = 0$. Thus

$$\sum_{ij}\int_\Omega \varepsilon_{ij}s_{ij}\,dx = c_{1111}\int_\Omega\left(\frac{\partial\phi_1}{\partial x_2} - \frac{\partial\phi_2}{\partial x_1}\right)(s_{11}+s_{22})\,dx,$$

as claimed. Hence $\int_\Omega \operatorname{curl}\phi \operatorname{Tr} s\,dx = 0$, which by the sufficiency of equation (9) in the Donati lemma, guarantees the existence of some $v \in H^1(\Omega)^2$ such that the given σ comes from v. Since this condition does not depend on the elasticity tensor, the displacement field v for any supposed elasticity tensor can be recovered by using the same ϕ, which proves the first assertion (i).

We turn to (ii) and note that by isotropy $\Delta c_{1111} = \Delta c_{1122} + 2\Delta c_{1212} = 0$. By the calculation in (i), we thus have

$$\Delta \sum_{ij} \varepsilon_{ij} s_{ij} = 2\Delta c_{1212} \left(\frac{\partial \phi_2}{\partial x_1} s_{11} + \frac{\partial \phi_2}{\partial x_2} s_{12} - \frac{\partial \phi_1}{\partial x_1} s_{12} - \frac{\partial \phi_1}{\partial x_2} s_{22} \right).$$

Since Δc_{1212} is constant, we conclude that

$$\Delta \sum_{ij} \int_\Omega \varepsilon_{ij} s_{ij} \, dx = 0,$$

which shows the claimed independence.

We consider now the case when the condition on the data is relaxed, but a is constant and $\Delta(c_{1122}/c_{1111}) = 0$. Since $\sum_i \langle \sigma\nu, 1\rangle_{\Gamma_i} = 0$, the stress field σ exists with components in $L^2(\Omega)$ and by the Helmholtz decomposition (8) there exist ϕ, $q \in H^1(\Omega)^2$ such that

$$\begin{pmatrix} \sigma_{11} & \sigma_{12} \\ \sigma_{12} & \sigma_{22} \end{pmatrix} = \begin{pmatrix} \frac{\partial \phi_1}{\partial x_2} & -\frac{\partial \phi_1}{\partial x_1} \\ \frac{\partial \phi_2}{\partial x_2} & -\frac{\partial \phi_2}{\partial x_1} \end{pmatrix} + \nabla q.$$

By the necessity of equation (9), we have for any s as above, that

$$0 = -\sum_{ij} \int_\Omega \varepsilon_{ij} s_{ij} \, dx = c_{1111} \int_\Omega \operatorname{curl} \phi \operatorname{Tr} s \, dx - c_{1122} \int_\Omega \operatorname{div} q \operatorname{Tr} s \, dx. \qquad (11)$$

Provided $\langle \sigma\nu, 1\rangle_{\Gamma_i} \neq 0$ for some i, the equation (11) holds independently of the elasticity tensor if and only if $\Delta(c_{1122}/c_{1111}) = 0$, since $\operatorname{div} q = 0$ gives self-equilibriated holes, $\langle \sigma\nu, 1\rangle_{\Gamma_i} = 0$. Thus, in general, then and only then there exists a displacement field $v \in H^1(\Omega)^2$ coming from σ, by the Donati lemma (9). ☐

Remark 9. *The property (ii) in Lemma 5 means invariance of the stress in the studied boundary value problem under the family of maps*

$$\left(\frac{1}{K}, \frac{1}{G} \right) \mapsto \left(\frac{1}{K} + \rho, \frac{1}{G} - \rho \right), \qquad -\frac{1}{K} < \rho < \frac{1}{G},$$

where K and G denote the planar bulk modulus and the shear modulus. This particular invariance was investigated in [6]. We refer the reader to [18, 19] for a thorough study of invariance of solutions in planar elasticity. Moreover, the fraction c_{1122}/c_{1111} is an elementary function of K/G, as well as of the Lamé ratio λ/μ, which are canonical parameters in planar linear elasticity. See [16, 18]).

Now we are in a position to prove the main result.

Proof of Theorem 1. By the hypothesis of positive definiteness on $\mathbf{R}^3$ of a^* defined by equation (1), a^* is nonsingular since by the definition it is symmetric. Hence, for every average stress there exist a unique stress field σ that, by the Michell lemma (Lemma 5), does not depend on the isotropic local elasticity tensor $a \in E$. For the boundary of any hole in the global problem is stress-free and hence the average normal stress on the outer part Γ_0 of the boundary of Ω

vanishes by the Green formula. The corresponding quasiperiodic displacement field u is unique up to translation. Thus the quasiperiod $\xi \in \mathbf{R}^3$ of u is uniquely determined by σ and a.

Let $\langle \sigma \rangle$ denote the average stress $|Y|^{-1} \int_\Omega (\sigma_{11}, \sigma_{22}, \sigma_{12})\, dx$, which we will let vary over the canonical basis f_i of $\mathbf{R}^3$. With $\langle \sigma \rangle = f_1$, equation (1) gives $c^*_{1111} = ((a^*)^{-1})_{1111} = \xi_{11}$. Since a is isotropic, $\xi \in \mathbf{R}^3$, and $\operatorname{div} \sigma$ vanishes, there exists by Lemma 3 a real constant d_{1111}, which depends only on σ and hence not on a, such that $c^*_{1111} = c_{1111}\, d_{1111}$. Moreover, by the same equation, there exists constants d_{1122} and d_{1112} such that $c^*_{1122} = -2c_{1212} + c_{1111}\, d_{1122}$ and $c^*_{1112} = c_{1111}\, d_{1112}$. With $\langle \sigma \rangle = f_2$, we similarly find constants d_{2222} and d_{2212} such that $c^*_{2222} = c_{1111}\, d_{2222}$ and $c^*_{2212} = c_{1111}\, d_{2212}$. Finally, with $\langle \sigma \rangle = f_3$, we find a constant d_{1212} such that $c^*_{1212} = c_{1212} + c_{1111}\, d_{1212}$. Let $d \in \mathbf{R}^6$ with components d_{ijkl} defined as above and extended by zero, up to the triclinic symmetry. Let $e \in \mathbf{R}^6$ be defined by $e_{1212} = -2e_{1122} = 1$, with the other components set to zero. Then $c^* = c_{1111}\, d + c_{1212}\, e$, where d and e do not depend on a by construction.

We argue in the same way for the case when a is changed in such a way that $\Delta c_{1122} = -2\Delta c_{1212} =$ constant. First, we have $\Delta c_{1111} = 0$ by isotropy, and by the assumption of uniform shift of the not necessarily constant compliance tensor c, the stress is invariant by (ii) in the Michell lemma. By Lemma 4, we have $\Delta c^*_{1111} = \Delta \xi_{11} = 0$, $\Delta c^*_{1122} = -2\Delta c_{1212} = \Delta c_{1122}$, and $\Delta c^*_{1112} = 0$, for $\langle \sigma \rangle = f_1$. For $\langle \sigma \rangle = f_2$, we find $\Delta c^*_{2222} = 0$ and $\Delta c^*_{2212} = 0$. Finally, we find $\Delta c^*_{1212} = \Delta c_{1212}$ for $\langle \sigma \rangle = f_3$. Hence, $\Delta c^* = \Delta c_{1212}\, e = \Delta c$. $\square$

4 Representations of geometric moduli

For computational purpose it may be worthwhile to document some representations of the geometric constants d_{ijkl}. In the proof of Theorem 1 the constants were represented in terms of average values of the stress field for some given global average stress. The reason for this was that we were interested in finding constants that were indepentent of the local elastic moduli by virtue of the Michell lemma. If we want to calculate the geometric constants however, it may be more convenient to start by specifying the quasiperiod and then calculate the average stress. This is because a numerical method, as for example a finite element method, would then be completely explicit. For this purpose we prove the following lemma, in which the geometric tensor d_{ijkl} is represented by a symmetric matrix D in $\mathbf{R}^6$ as described in Remark 3. Here we will use the notation $\langle f \rangle = \frac{1}{|Y|} \int_\Omega f\, dx$ to denote the weighted average value of a function over the periodicity cell Ω.

Lemma 6. *Let the local elasticity tensor be the diagonal element in E with $K = G = 1/2$. Let σ^a, σ^b, σ^c be the stress fields corresponding to the respective ξ^a, ξ^b, ξ^c quasiperiodic minimizers of $\int_\Omega \varepsilon \cdot \sigma\, dx$, where ξ^a, ξ^b, ξ^c is set to be the* *canonical basis of* $\mathbf{R}^3$. *Then*

$$\begin{aligned}
D_1 &= \mu^{-1}(\langle\sigma^b_{12}\rangle^2 - \langle\sigma^c_{12}\rangle\langle\sigma^b_{22}\rangle),\\
D_2 &= \mu^{-1}(\langle\sigma^a_{22}\rangle\langle\sigma^c_{12}\rangle - \langle\sigma^a_{12}\rangle\langle\sigma^b_{12}\rangle - \langle\sigma^a_{11}\rangle\langle\sigma^c_{12}\rangle\langle\sigma^b_{22}\rangle\\
&\qquad + \langle\sigma^a_{11}\rangle\langle\sigma^b_{12}\rangle^2 + \langle\sigma^a_{22}\rangle^2\langle\sigma^c_{12}\rangle + \langle\sigma^b_{22}\rangle\langle\sigma^a_{12}\rangle^2 - 2\langle\sigma^a_{12}\rangle\langle\sigma^a_{22}\rangle\langle\sigma^b_{12}\rangle),\\
D_3 &= \mu^{-1}(\langle\sigma^a_{12}\rangle\langle\sigma^b_{22}\rangle - \langle\sigma^b_{12}\rangle\langle\sigma^a_{22}\rangle),\\
D_4 &= \mu^{-1}(\langle\sigma^a_{12}\rangle^2 - \langle\sigma^c_{12}\rangle\langle\sigma^a_{11}\rangle),\\
D_5 &= \mu^{-1}(\langle\sigma^b_{12}\rangle\langle\sigma^a_{11}\rangle - \langle\sigma^a_{12}\rangle\langle\sigma^a_{22}\rangle),\\
D_6 &= \mu^{-1}(\langle\sigma^a_{22}\rangle^2 - \langle\sigma^b_{22}\rangle\langle\sigma^a_{11}\rangle - 2\langle\sigma^a_{11}\rangle\langle\sigma^c_{12}\rangle\langle\sigma^b_{22}\rangle\\
&\qquad - 2\langle\sigma^a_{11}\rangle\langle\sigma^b_{12}\rangle^2 - 2\langle\sigma^a_{22}\rangle^2\langle\sigma^c_{12}\rangle - 2\langle\sigma^b_{22}\rangle\langle\sigma^a_{12}\rangle^2 + 4\langle\sigma^a_{12}\rangle\langle\sigma^a_{22}\rangle\langle\sigma^b_{12}\rangle),
\end{aligned}$$

where μ *is the nonzero real number defined by the equation*

$$\frac{\mu}{4} = \langle\sigma^a_{11}\rangle\langle\sigma^b_{12}\rangle^2 - \langle\sigma^a_{11}\rangle\langle\sigma^c_{12}\rangle\langle\sigma^b_{22}\rangle + \langle\sigma^a_{22}\rangle^2\langle\sigma^c_{12}\rangle + \langle\sigma^b_{22}\rangle\langle\sigma^a_{12}\rangle^2 - 2\langle\sigma^a_{12}\rangle\langle\sigma^a_{22}\rangle\langle\sigma^b_{12}\rangle.$$

Proof. For $\xi \in \mathbf{R}^3$, the effective relation (1) can by Theorem 1 and Remark 3, be written as

$$\frac{1}{|Y|}\int_\Omega (\sigma_{11}, \sigma_{22}, \sigma_{12})\, dx = A^*(\xi_{11}, \xi_{22}, 2\xi_{12}),$$

where A^* is the inverse of the nonsingular matrix

$$\left(\frac{1}{K} + \frac{1}{G}\right)\begin{pmatrix} D_1 & D_2 & D_3\\ D_2 & D_4 & D_5\\ D_3 & D_5 & D_6 \end{pmatrix} + \frac{1}{G}\begin{pmatrix} 0 & -1/2 & 0\\ -1/2 & 0 & 0\\ 0 & 0 & 1 \end{pmatrix}.$$

By letting ξ vary over the canonical basis of $\mathbf{R}^3$ we obtain a system of linear equations in the components of D:

$$B(D_1, \dots, D_6) = \frac{1}{|Y|}\int_\Omega (\sigma^a_{11}, \sigma^a_{22}, \sigma^a_{12}, \sigma^b_{22}, \sigma^b_{12}, \sigma^c_{12})\, dx$$

This system is uniquely solvable with solution D given explicitly by the equations in the statement of the lemma. ☐

Remark 10. *The reason for the supposition that* $K = G = 1/2$ *in Lemma 6 is only notational convenience. The same argument gives the corresponding representation for arbitrary* K, $G > 0$. *Also, for numerical calculations it may be convenient to have a local elasticity tensor which is diagonal, which here corresponds to zero Poisson ratio in a planar model.*

We document the representations found in the proof of Theorem 1 in the form of a lemma.

Lemma 7. *Let* K *and* G *be the local elastic moduli. Let* σ^a, σ^b, σ^c *and* ξ^a, ξ^b, ξ^c *be the stress fields and quasiperiods corresponding to the quasiperiodic minimizers of* $\int_\Omega \varepsilon \cdot \sigma\, dx$ *with average stress* $\langle\sigma\rangle$ *equal to* $(1, 0, 0)$, $(0, 1, 0)$, $(0, 0, 1)$, *respectively. Then*

$$
\begin{aligned}
D_1 &= \frac{1}{4l_1}\int_{\gamma_1} ((\operatorname{Tr}\sigma^a, 0) - x_2 \operatorname{curl}\operatorname{Tr}\sigma^a)\, dx,\\
D_2 &= \frac{1}{4l_2}\int_{\gamma_2} ((0, \operatorname{Tr}\sigma^a) - x_1 \operatorname{curl}\operatorname{Tr}\sigma^a) dx = \frac{1}{4l_1}\int_{\gamma_1} ((\operatorname{Tr}\sigma^b, 0) - x_2 \operatorname{curl}\operatorname{Tr}\sigma^b) dx,\\
D_3 &= \frac{1}{4l_1}\int_{\gamma_1} ((\operatorname{Tr}\sigma^a, 0) + x_1 \operatorname{curl}\operatorname{Tr}\sigma^a) dx + \frac{1}{4l_2}\int_{\gamma_2} ((0, \operatorname{Tr}\sigma^a) - x_2 \operatorname{curl}\operatorname{Tr}\sigma^a) dx\\
&= \frac{1}{4l_1}\int_{\gamma_1} ((\operatorname{Tr}\sigma^c, 0) - x_2 \operatorname{curl}\operatorname{Tr}\sigma^c)\, dx,\\
D_4 &= \frac{1}{4l_2}\int_{\gamma_2} ((0, \operatorname{Tr}\sigma^b) + x_1 \operatorname{curl}\operatorname{Tr}\sigma^b)\, dx,\\
D_5 &= \frac{1}{4l_2}\int_{\gamma_2} ((0, \operatorname{Tr}\sigma^c) + x_1 \operatorname{curl}\operatorname{Tr}\sigma^c)\, dx,\\
D_6 &= \frac{1}{4l_1}\int_{\gamma_1} ((\operatorname{Tr}\sigma^c, 0) + x_1 \operatorname{curl}\operatorname{Tr}\sigma^c)\, dx + \frac{1}{4l_2}\int_{\gamma_2} ((0, \operatorname{Tr}\sigma^c) - x_2 \operatorname{curl}\operatorname{Tr}\sigma^c)\, dx.
\end{aligned}
$$

We conclude this section with a remark on a representation that can be used for numerical calculations. We will write the geometric constants in terms of the average elastic energies of the solutions to the cell problems. Consider the following cell problems with ξ^i denoting the "average strain":

$$
\begin{aligned}
\xi^1 &= (1,0,0), & \xi^2 &= (0,1,0), & \xi^3 &= (0,0,1),\\
\xi^4 &= (1,1,0), & \xi^5 &= (0,1,1), & \xi^6 &= (1,0,1).
\end{aligned}
$$

Let u^i denote the solution to equation (1) with $\xi = \xi^i$ and let B^* denote the effective elasticity tensor in the notation of Remark 3. First, with

$$
\mathcal{E}_{ij} = \frac{1}{|Y|}\int_\Omega \varepsilon(u^i)\cdot B\varepsilon(u^j)\, dx,
$$

we have

$$
\begin{pmatrix} B_1^* & B_2^* & B_3^* \\ B_2^* & B_4^* & B_5^* \\ B_3^* & B_5^* & B_6^* \end{pmatrix} = \begin{pmatrix} \mathcal{E}_{11} & \mathcal{E}_{12} & \mathcal{E}_{13} \\ \mathcal{E}_{12} & \mathcal{E}_{22} & \mathcal{E}_{23} \\ \mathcal{E}_{13} & \mathcal{E}_{23} & \mathcal{E}_{33} \end{pmatrix}.
$$

By the equation in Remark 3, the entries of the matrix D can then be calculated. Here, only the the diagonal entries of the matrix B^* were expressed as energies of the solutions to the cell problems. We observe that, by the definition of the effective elasticity tensor,

$$
\begin{aligned}
\mathcal{E}_{11} &= B_1^*, & \mathcal{E}_{22} &= B_4^*, & \mathcal{E}_{33} &= B_6^*,\\
\mathcal{E}_{44} &= B_1^* + 2B_2^* + B_4^*, & \mathcal{E}_{55} &= B_4^* + 2B_5^* + B_6^*, & \mathcal{E}_{66} &= B_1^* + 2B_3^* + B_6^*.
\end{aligned}
$$

By linearity we can find u^4, u^5, and u^6, from u^1, u^2, and u^3. Moreover, it follows that

$$
\begin{aligned}
B_1^* &= \mathcal{E}_{11}, & B_2^* &= \frac{\mathcal{E}_{44} - \mathcal{E}_{11} - \mathcal{E}_{22}}{2}, & B_3^* &= \frac{\mathcal{E}_{66} - \mathcal{E}_{11} - \mathcal{E}_{33}}{2},\\
B_4^* &= \mathcal{E}_{22}, & B_5^* &= \frac{\mathcal{E}_{55} - \mathcal{E}_{22} - \mathcal{E}_{33}}{2}, & B_6^* &= \mathcal{E}_{33},
\end{aligned}
$$

which is now explicitly written in terms of the average elastic energies $\mathcal{E}_{ii}/2$ of the solutions u^i to the cell problems. Finally, the representation obtained for the geometric elastic modulus D is therefore

$$D = \frac{KG}{K+G}\left(\begin{pmatrix} 2\epsilon_1 & \epsilon_4-\epsilon_1-\epsilon_2 & \epsilon_6-\epsilon_1-\epsilon_3 \\ \epsilon_4-\epsilon_1-\epsilon_2 & 2\epsilon_2 & \epsilon_5-\epsilon_2-\epsilon_3 \\ \epsilon_6-\epsilon_1-\epsilon_3 & \epsilon_5-\epsilon_2-\epsilon_3 & 2\epsilon_3 \end{pmatrix}^{-1} + \frac{1}{G}\begin{pmatrix} 0 & \frac{1}{2} & 0 \\ \frac{1}{2} & 0 & 0 \\ 0 & 0 & -1 \end{pmatrix}\right),$$

where $\epsilon_i = \mathcal{E}_{ii}/2$ denotes the average elastic energy for the solution u^i with quasiperiod ξ^i.

5 Numerical example

Consider a periodic symmetric material structure consisting of one isotropic material of Young modulus $E = 1$ with Poisson ratio ν (for example a plane strain model), which is perforated in a periodic manner. In Figure 3 one period (cell) of this material structure is illustrated.

Due to the mirror symmetry in the cell and the local elasticity tensor, the effective elasticity tensor is[10] orthotropic, that is the effective stiffness matrix B^* is of the form

$$B^* = \begin{pmatrix} B_1^* & B_2^* & 0 \\ B_2^* & B_4^* & 0 \\ 0 & 0 & B_6^* \end{pmatrix}.$$

We may, again by symmetry[11], solve the cell-problem on one half of the cell (see Figure 4), and we set $Y = (0,1)^2$.

To find the parameter B_1^* we use the following Dirichlet boundary conditions:

$$\xi = \xi^1 : \quad u_1(0,x_2) = u_2(x_1,0) = u_2(x_1,1) = 0, \qquad u_1(1,x_2) = 1,$$

which, as indicated, correspond to $\xi = \xi^1 = (1,0,0)$ as in the end of the previous section. That means that B_1^* is equal to two times the average elastic energy. Similarly, to find the other parameters we use the following boundary conditions:

$$\begin{aligned} \xi = \xi^2 : &\quad u_2(x_1,0) = u_1(0,x_2) = u_1(1,x_2) = 0, && u_2(x_1,1) = 1, \\ \xi = \xi^3 : &\quad u_2(0,x_2) = u_1(x_1,0) = 0, && u_2(1,x_2) = u_1(x_1,1) = 1/2, \\ \xi = \xi^4 : &\quad u_1(0,x_2) = u_2(x_1,0) = 0, && u_1(1,x_2) = u_2(x_1,1) = 1. \end{aligned}$$

After the energies $\epsilon_1, \ldots, \epsilon_4$ have been calculated, we can use the formula for D given at the very end of the previous section.

The numerical solutions are obtained by using the finite element software ANSYS[12] with the plane strain model. This means that (E,ν) and (K,G) are here related as described in Remark 3. We have used a 2D 8-node structural solid element called plane183 and the element mesh consists of 9936 elements and 30235 nodes, as seen in Figure 4. By finding the energy ϵ_i in the four cases described above we obtain the numerical values for the case $E = 1$ (for the general case one can just multiply the values of B_i^* given below by E), and these are presented in Table 1. From the untruncated data corresponding to Table 1 we find the numerical values of the parameters D_i by using the last equation in the previous section. These values are presented in Table 2. We observe that the numerical values of these parameters are almost independent of the Poisson ratio, in agreement with our theoretical results.

---

[10] See Section 2 and the references given there.

[11] The reason for not choosing a smaller part of the domain is just for notational convenience. Actually, all computations can be carried out on the restriction to one-fourth of the cell shown in Figure 3, for example $(0,1) \times (0,1/2)$. This is because the order of the symmetry group Dih_2 is 4. Moreover, the group is commutative so the equations will also then decouple.

[12] Version 12.2.

ν	10^{-6}	10^{-4}	0.1	0.2	0.3	0.4	0.49
B_1^*	0.756	0.756	0.776	0.835	0.970	1.324	2.716
B_4^*	0.806	0.806	0.827	0.890	1.034	1.412	2.894
B_2^*	0.037	0.037	0.107	0.209	0.382	0.775	2.233
B_6^*	0.309	0.309	0.292	0.279	0.268	0.260	0.255

Table 1: The numerical values (truncated) of the entries of B^* obtained from ANSYS.

ν	10^{-6}	10^{-4}	0.1	0.2	0.3	0.4	0.49
D_1	0.33123	0.33125	0.33125	0.33123	0.33123	0.33125	0.33120
D_2	0.23466	0.23466	0.23466	0.23466	0.23466	0.23464	0.23468
D_4	0.31078	0.31078	0.31078	0.31078	0.31078	0.31080	0.31078
D_6	0.30835	0.30835	0.30835	0.30835	0.30833	0.30833	0.30835

Table 2: The numerical values (rounded) of the entries of D for the various Poisson ratios obtained from the untruncated data corresponding to Table 1.



Figure 3: The cell of periodicity is a 2×1 rectangle with a hole of radius 1/4 in the center of the cell.



Figure 4: One half of the cell.

References

[1] *Handbuch der Physik. Band VIa/2: Festkörpermechanik. II.* Springer-Verlag, Berlin, 1972. Herausgegeben von S. Flügge; Bandherausgeber: C. Truesdell.

[2] *Handbuch der Physik. Band VIa/1: Festkörpermechanik. I.* Springer-Verlag, Berlin, 1973. Herausgegeben von S. Flügge; Bandherausgeber: C. Truesdell.

[3] C. Amrouche, P. G. Ciarlet, G. Liliana, and K. Srinivasan. On the characterizations of matrix fields as linearized strain tensor fields. *J. Math. Pures Appl. (9)*, 86(2):116–132, 2006.

[4] S. A. Berggren, D. Lukkassen, A. Meidell, and L. Simula. Some methods for calculating stiffness properties of periodic structures. *Appl. Math.*, 48(2):97–110, 2003.

[5] A. Bossavit. Symmetry, groups, and boundary value problems. A progressive introduction to noncommutative harmonic analysis of partial differential equations in domains with geometrical symmetry. *Computer Methods in Applied Mechanics and Engineering*, 56(2):167–215, 1986.

[6] A. V. Cherkaev, K. A. Lurie, and G. W. Milton. Invariant properties of the stress in plane elasticity and equivalence classes of composites. *Proc. Roy. Soc. London Ser. A*, 438(1904):519–529, 1992.

[7] P. G. Ciarlet and P. Ciarlet, Jr. Another approach to linearized elasticity and a new proof of Korn's inequality. *Math. Models Methods Appl. Sci.*, 15(2):259–271, 2005.

[8] L. Donati. Illustrazione al teorema del menabrea. *Mem. Accad. Sci. Bologna*, 4(10):267–274, 1890.

[9] G. Fichera. Existence theorems in elasticity. *Handbuch der Physik*, VIa/2:347–424, 1972.

[10] M. Fréchet. Sur les ensembles de fonctions et les opérations linéaires. *C. R. Acad. Sci. Paris*, 144:1414–1416, 1907.

[11] V. Girault and P.-A. Raviart. *Finite element methods for Navier-Stokes equations*, volume 5 of *Springer Series in Computational Mathematics.* Springer-Verlag, Berlin, 1986. Theory and algorithms.

[12] M. E. Gurtin. The linear theory of elasticity. *Handbuch der Physik*, VIa/2:1–273, 1972.

[13] D. Lukkassen, A. Meidell, and K. Pettersson. An elementary proof of the Vigdergauz equations for a class of square symmetric structures. *Preprint*, arXiv:1204.6419, 2012.

[14] D. Lukkassen, A. Meidell, and S. Vigdergauz. On the elastic deformation of symmetric periodic structures. *Quart. J. Mech. Appl. Math.*, 56(3):441–454, 2003.

[15] J. H. Michell. On the direct determination of stress in an elastic solid, with application to the theory of plates. *Proceedings of the London Mathematical Society*, 31(36):100–124, 1899.

[16] N. I. Muskhelishvili. *Some basic problems of the mathematical theory of elasticity. Fundamental equations, plane theory of elasticity, torsion and bending.* P. Noordhoff Ltd., Groningen, 1953. Translated by J. R. M. Radok.

[17] O. A. Oleĭnik, A. S. Shamaev, and G. A. Yosifian. *Mathematical problems in elasticity and homogenization*, volume 26 of *Studies in Mathematics and its Applications*. North-Holland Publishing Co., Amsterdam, 1992.

[18] P. J. Olver. Canonical elastic moduli. *Journal of elasticity*, 19(3):189–212, 1988.

[19] P. J. Olver. The equivalence problem and canonical forms for quadratic lagrangians. *Advances in Applied Mathematics*, 9(2):226–257, 1988.

[20] K. Pettersson. *Homogenization of some elliptic equations with connections to elasticity.* Doctoral thesis, Luleå University Of Technology, Luleå, Sweden, December 2010.

[21] F. Riesz. Sur une espèce de géométrie analytique des systèmes de fonctions sommables. *C. R. Acad. Sci. Paris*, 144:1409–1411, 1907.

[22] J.-P. Serre. *Linear representations of finite groups.* Springer-Verlag, New York, 1977. Translated from the second French edition by Leonard L. Scott, Graduate Texts in Mathematics, Vol. 42.

[23] T. W. Ting. St. Venant's compatibility conditions. *Tensor (N.S.)*, 28:5–12, 1974.

[24] S. Torquato. Random heterogeneous materials: Microstructure and macroscopic properties.

[25] S. Vigdergauz. Complete elasticity solution to the stress problem in a planar grained structure. *Math. Mech. Solids*, 4(4):407–439, 1999.